



(11) **EP 1 933 395 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:
25.05.2011 Bulletin 2011/21

(51) Int Cl.:
H01L 51/30^(2006.01) **C09K 11/06^(2006.01)**
H05B 33/14^(2006.01)

(21) Application number: **08003327.7**

(22) Date of filing: **29.11.2000**

(54) **Complexes of form L2IrX**

Komplex der Formel L2IrX

Complexes de formule L2IrX

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

(30) Priority: **01.12.1999 US 452346**

(43) Date of publication of application:
18.06.2008 Bulletin 2008/25

(60) Divisional application:
10181664.3 / 2 278 637
10181674.2 / 2 270 895

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
00980863.5 / 1 252 803

(73) Proprietors:
• **The Trustees of Princeton University**
Princeton, NJ 08544 (US)
• **The University of Southern California**
Los Angeles, CA 90007-4344 (US)

(72) Inventors:
• **Thompson, Mark E.**
Anaheim, CA 92807 (US)
• **Djurovich, Peter**
Long Beach
CA 90007 (US)
• **Lamansky, Sergey**
Apple Valley, MN 55214 (US)
• **Murphy, Drew**
New Haven, CT 06511 (US)
• **Kwong, Raymond**
New Jersey 08536 (US)
• **Abdel-Razzaq, Feras**
Los Angeles, CA 90089 (US)

• **Forrest, Stephen R.**
Ann Arbor
Michigan 48109 (US)
• **Baldo, Marc A.**
Cambridge, MA 02142 (US)
• **Burrows, Paul**
Kennewick, WA 99338 (US)

(74) Representative: **Kiriczi, Sven Bernhard**
Schneiders & Behrendt
Mühlthaler Strasse 91d
81475 München (DE)

(56) References cited:
WO-A-02/02714 WO-A-02/15645
US-A- 5 703 436

• **CALOGERO G. ET AL: "ABSORPTION SPECTRA; LUMINESCENCE PROPERTIES, AND ELECTROCHEMICAL BEHAVIOR OF CYCLOMETALATED IRIIDIUM (III) AND RHODIUM (III) COMPLEXES WITH A BIS(PYRIDYL) TRIAZOLE LIGAND" INORGANIC CHEMISTRY, AMERICAN CHEMICAL SOCIETY, EASTON, US, vol. 34, no. 3, 1 February 1995 (1995-02-01), pages 541-545, XP002231208 ISSN: 0020-1669**
• **MARCO DI G ET AL: "LUMINESCENT MONONUCLEAR AND DINUCLEAR IRIIDIUM(III) CYCLOMETALATED COMPLEXES IMMOBILIZED IN A POLYMERIC MATRIX AS SOLID-STATE OXYGEN SENSORS" ANALYTICAL CHEMISTRY, AMERICAN CHEMICAL SOCIETY, COLUMBUS, US, vol. 70, no. 23, 1 December 1998 (1998-12-01), pages 5019-5023, XP000799212 ISSN: 0003-2700**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 933 395 B1

- NEVE F ET AL: "SYNTHESIS, STRUCTURE, PHOTOPHYSICAL PROPERTIES, AND REDOX BEHAVIOUR OF CYCLOMETALATED COMPLEXES OF IRIIDIUM(III) WITH FUNCTIONALIZED 2,2'-BIPYRIDINES" INORGANIC CHEMISTRY, AMERICAN CHEMICAL SOCIETY, EASTON, US, vol. 38, no. 10, 17 May 1999 (1999-05-17), pages 2250-2258, XP002295198 ISSN: 0020-1669
- WILDE A P ET AL: "Resolution and analysis of the components in dual emission of mixed-chelate/ortho-metalate complexes of Iridium(III)" JOURNAL OF PHYSICAL CHEMISTRY, AMERICAN CHEMICAL SOCIETY, US, vol. 95, 1991, pages 629-634, XP002315391 ISSN: 0022-3654

Description**I. FIELD OF INVENTION**

5 **[0001]** The present invention relates to phosphorescent organometallic compounds of formula L_2IrX , wherein L and X are bidentate ligands.

II. BACKGROUND OF THE INVENTION

10 II. A. General Background

[0002] Organic light emitting devices (OLEDs) are comprised of several organic layers in which one of the layers is comprised of an organic material that can be made to electroluminesce by applying a voltage across the device, C.W. Tang et al., Appl. Phys. Lett. 1987, 51, 913. Certain OLEDs have been shown to have sufficient brightness, range of color and operating lifetimes for use as a practical alternative technology to LCD-based full color flat-panel displays (S.R. Forrest, P.E. Burrows and M.E. Thompson, Laser Focus World, Feb. 1995). Since many of the thin organic films used in such devices are transparent in the visible spectral region, they allow for the realization of a completely new type of display pixel in which red (R), green (G), and blue (B) emitting OLEDs are placed in a vertically stacked geometry to provide a simple fabrication process, a small R-G-B pixel size, and a large fill factor, International Patent Application No. PCT/US95/15790.

[0003] A transparent OLED (TOLED), which represents a significant step toward realizing high resolution, independently addressable stacked R-G-B pixels, was reported in International Patent Application No. PCT/US97/02681 in which the TOLED had greater than 71% transparency when turned off and emitted light from both top and bottom device surfaces with high efficiency (approaching 1% quantum efficiency) when the device was turned on. The TOLED used transparent indium tin oxide (ITO) as the hole-injecting electrode and a Mg-Ag-ITO electrode layer for electron-injection. A device was disclosed in which the ITO side of the Mg-Ag-ITO layer was used as a hole-injecting contact for a second, different color-emitting OLED stacked on top of the TOLED. Each layer in the stacked OLED (SOLED) was independently addressable and emitted its own characteristic color. This colored emission could be transmitted through the adjacently stacked, transparent, independently addressable, organic layer or layers, the transparent contacts and the glass substrate, thus allowing the device to emit any color that could be produced by varying the relative output of the red and blue color-emitting layers.

[0004] PCT/US95/15790 application disclosed an integrated SOLED for which both intensity and color could be independently varied and controlled with external power supplies in a color tunable display device. The PCT/US95/15790 application, thus, illustrates a principle for achieving integrated, full color pixels that provide high image resolution, which is made possible by the compact pixel size. Furthermore, relatively low cost fabrication techniques, as compared with prior art methods, may be utilized for making such devices.

II.B. Background of emission

40 II.B.1. Basics

II.B.1.a. Singlet and Triplet Excitons

[0005] Because light is generated in organic materials from the decay of molecular excited states or excitons, understanding their properties and interactions is crucial to the design of efficient light emitting devices currently of significant interest due to their potential uses in displays, lasers, and other illumination applications. For example, if the symmetry of an exciton is different from that of the ground state, then the radiative relaxation of the exciton is disallowed and luminescence will be slow and inefficient. Because the ground state is usually anti-symmetric under exchange of spins of electrons comprising the exciton, the decay of a symmetric exciton breaks symmetry. Such excitons are known as triplets, the term reflecting the degeneracy of the state. For every three triplet excitons that are formed by electrical excitation in an OLED, only one symmetric state (or singlet) exciton is created. (M.A. Baldo, D. F. O'Brien, M.E. Thompson and S. R. Forrest, Very high-efficiency green organic light-emitting devices based on electrophosphorescence, Applied Physics Letters, 1999, 75, 4-6.) Luminescence from a symmetry-disallowed process is known as phosphorescence. Characteristically, phosphorescence may persist for up to several seconds after excitation due to the low probability of the transition. In contrast, fluorescence originates in the rapid decay of a singlet exciton. Since this process occurs between states of like symmetry, it may be very efficient.

[0006] Many organic materials exhibit fluorescence from singlet excitons. However, only a very few have been identified which are also capable of efficient room temperature phosphorescence from triplets. Thus, in most fluorescent dyes,

the energy contained in the triplet states is wasted. However, if the triplet excited state is perturbed, for example, through spin-orbit coupling (typically introduced by the presence of a heavy metal atom), then efficient phosphorescence is more likely. In this case, the triplet exciton assumes some singlet character and it has a higher probability of radiative decay to the ground state. Indeed, phosphorescent dyes with these properties have demonstrated high efficiency electroluminescence.


[0007] Only a few organic materials have been identified which show efficient room temperature phosphorescence from triplets. In contrast, many fluorescent dyes are known (C.H. Chen, J. Shi, and C.W. Tang, "Recent developments in molecular organic electroluminescent materials," *Macromolecular Symposia*, 1997, 125, 1-48; U. Brackmann, *Lambdachrome Laser Dyes* (Lambda Physik, Göttingen, 1997) and fluorescent efficiencies in solution approaching 100% are not uncommon. (C.H. Chen, 1997, op. cit.) Fluorescence is also not affected by triplet-triplet annihilation, which degrades phosphorescent emission at high excitation densities. (M. A. Baldo, et al., "High efficiency phosphorescent emission from organic electroluminescent devices," *Nature*, 1998, 395, 151-154; M. A. Baldo, M. E. Thompson, and S.R. Forrest, "An analytic model of triplet-triplet annihilation in electrophosphorescent devices," 1999). Consequently, fluorescent materials are suited to many electroluminescent applications, particularly passive matrix displays.

II.B.1.b. Overview of invention relative to basics

[0008] The invention is directed to L_2MX , wherein L and X are distinct bidentate ligands, wherein L coordinates to M via atoms of L comprising sp^2 hybridized carbon and heteroatoms, and wherein M is iridium (Ir). These compounds can serve as dopants in a host layer which functions as an emitter layer in organic light emitting diodes.

[0009] The compounds of this invention can be made by the direct reaction of chloride bridged dimers of the form $L_2M(\mu-Cl)_2ML_2$, wherein L a bidentate ligand, and M is Ir, with species XH which serve to introduce a bidentate ligand X. XH can be, for example, acetylacetone, 2-picolinic acid, or N-methylsalicyclanilide, and H stands for hydrogen. The resultant product is of formula L_2MX , wherein one can have an octahedral disposition of the bidentate ligands L, L, and X about M.

[0010] The resultant compounds of formula L_2MX can be used as phosphorescent emitters in organic light emitting devices. For example, the compound wherein $L=(2\text{-phenylbenzothiazole})$, $X=\text{acetylacetonate}$, and $M=\text{Ir}$ (the compound abbreviated as BTIr) when used as a dopant in 4,4'-N,N'-dicarbazole-biphenyl (CBP)(at a level 12% by mass) to form an emitter layer in an OLED shows a quantum efficiency of 12%. For reference, the formula CBP is



[0011] The synthetic process to make L_2MX may be used advantageously in a situation in which L, by itself, is fluorescent but the resultant L_2MX is phosphorescent. One specific example of this is where $L=\text{coumarin-6}$.

[0012] The synthetic process facilitates the combination of L and X pairs of certain desirable characteristics.

[0013] The appropriate selection of L and X allows color tuning of the complex L_2MX relative to L_3M . For example, $\text{Ir}(\text{ppy})_3$ and $(\text{ppy})_2\text{Ir}(\text{acac})$ both give strong green emission with a λ_{max} of 510 nm [ppy denotes phenyl pyridine]. However, if the X ligand is formed from picolinic acid instead of from acetylacetone, there is a small blue shift of about 15 nm.

[0014] Furthermore, X can be selected such that it has a certain HOMO level relative to the L_3M complex so that carriers (holes or electrons) might be trapped on X (or on L) without a deterioration of emission quality. In this way, carriers (holes or electrons) which might otherwise contribute to deleterious oxidation or reduction of the phosphor would be impeded. The carrier that is remotely trapped could readily recombine with the opposite carrier either intramolecularly or with the carrier from an adjacent molecule.

[0015] The invention, and its various embodiments, are discussed in more detail in the examples below. However the embodiments may operate by different mechanisms. Without limitation and without limiting the scope of the invention, we discuss the different mechanisms by which various embodiments of the invention may operate.

II.B.1.c. Dexter and Förster mechanisms

[0016] To understand the different embodiments of this invention it is useful to discuss the underlying mechanistic theory of energy transfer. There are two mechanisms commonly discussed for the transfer of energy to an acceptor molecule. In the first mechanism of Dexter transport (D.L. Dexter, "A theory of sensitized luminescence in solids," J.

Chem. Phys., 1953, 21, 836-850), the exciton may hop directly from one molecule to the next. This is a short-range process dependent on the overlap of molecular orbitals of neighboring molecules. It also preserves the symmetry of the donor and acceptor pair (E. Wigner and E.W. Wittmer, *Über die Struktur der zweiatomigen Molekülspektren nach der Quantenmechanik*, Zeitschrift für Physik, 1928, 51, 859-886; M. Klessinger and J. Michl, *Excited states and photochemistry of organic molecules* (VCH Publishers, New York, 1995). Thus, the energy transfer of Eq. (1) is not possible via Dexter mechanism. In the second mechanism of Förster transfer (T. Förster, *Zwischenmolekulare Energiewanderung und Fluoreszenz*, Annalen der Physik, 1948, 2, 55-75; T. Förster, *Fluoreszenz organischer Verbindungen* (Vandenhoeck and Ruprecht, Göttingen, 1951), the energy transfer of Eq. (1) is possible. In Förster transfer, similar to a transmitter and an antenna, dipoles on the donor and acceptor molecules couple and energy may be transferred. Dipoles are generated from allowed transitions in both donor and acceptor molecules. This typically restricts the Förster mechanism to transfers between singlet states.

[0017] Nevertheless, as long as the phosphor can emit light due to some perturbation of the state such as due to spin-orbit coupling introduced by a heavy metal atom, it may participate as the donor in Förster transfer. The efficiency of the process is determined by the luminescent efficiency of the phosphor (F Wilkinson, in *Advances in Photochemistry* (eds. W.A. Noyes, G. Hammond, and J.N. Pitts, pp. 241-268, John Wiley & Sons, New York, 1964), i.e. if a radiative transition is more probable than a non-radiative decay, then energy transfer will be efficient. Such triplet-singlet transfers were predicted by Förster (T. Förster, "Transfer mechanisms of electronic excitation," *Discussions of the Faraday Society*, 1959, 27, 7-17) and confirmed by Ermolaev and Sveshnikova (V.L. Ermolaev and E. B. Sveshnikova, "Inductive-resonance transfer of energy from aromatic molecules in the triplet state," *Doklady Akademii Nauk SSSR*, 1963, 149, 1295-1298), who detected the energy transfer using a range of phosphorescent donors and fluorescent acceptors in rigid media at 77K or 90K. Large transfer distances are observed; for example, with triphenylamine as the donor and chrysoidine as the acceptor, the interaction range is 52Å.

[0018] The remaining condition for Förster transfer is that the absorption spectrum should overlap the emission spectrum of the donor assuming the energy levels between the excited and ground state molecular pair are in resonance. In Example 1 of this application, we use the green phosphor fac tris(2-phenylpyridine) iridium ($\text{Ir}(\text{ppy})_3$; M. A. Baldo, et al., *Appl. Phys. Lett.*, 1999, 75, 4-6) and the red fluorescent dye [2-methyl-6-[2-(2,3,6,7-tetrahydro-1H,5H-benzo[*ij*]quinolizin-9-yl) ethenyl]-4H-pyran-ylidene] propane-dinitrile ("DCM2"; C. W. Tang, S. A. VanSlyke, and C. H. Chen, "Electroluminescence of doped organic films," *J. Appl. Phys.*, 1989, 65, 3610-3616). DCM2 absorbs in the green, and, depending on the local polarization field (V. Bulovic, et al., "Bright, saturated, red-to-yellow organic light-emitting devices based on polarization-induced spectral shifts," *Chem. Phys. Lett.*, 1998, 287, 455-460), it emits at wavelengths between $\lambda=570$ nm and $\lambda=650$ nm.

[0019] It is possible to implement Förster energy transfer from a triplet state by doping a fluorescent guest into a phosphorescent host material. Unfortunately, such systems are affected by competitive energy transfer mechanisms that degrade the overall efficiency. In particular, the close proximity of the host and guest increase the likelihood of Dexter transfer between the host to the guest triplets. Once excitons reach the guest triplet state, they are effectively lost since these fluorescent dyes typically exhibit extremely inefficient phosphorescence.

[0020] To maximize the transfer of host triplets to fluorescent dye singlets, it is desirable to maximize Dexter transfer into the triplet state of the phosphor while also minimizing transfer into the triplet state of the fluorescent dye. Since the Dexter mechanism transfers energy between neighboring molecules, reducing the concentration of the fluorescent dye decreases the probability of triplet-triplet transfer to the dye. On the other hand, long range Förster transfer to the singlet state is unaffected. In contrast, transfer into the triplet state of the phosphor is necessary to harness host triplets, and may be improved by increasing the concentration of the phosphor.

II.B.2. Interrelation of device structure and emission

[0021] Devices whose structure is based upon the use of layers of organic optoelectronic materials generally rely on a common mechanism leading to optical emission. Typically, this mechanism is based upon the radiative recombination of a trapped charge. Specifically, OLEDs are comprised of at least two thin organic layers separating the anode and cathode of the device. The material of one of these layers is specifically chosen based on the material's ability to transport holes, a "hole transporting layer" (HTL), and the material of the other layer is specifically selected according to its ability to transport electrons, an "electron transporting layer" (ETL). With such a construction, the device can be viewed as a diode with a forward bias when the potential applied to the anode is higher than the potential applied to the cathode. Under these bias conditions, the anode injects holes (positive charge carriers) into the hole transporting layer, while the cathode injects electrons into the electron transporting layer. The portion of the luminescent medium adjacent to the anode thus forms a hole injecting and transporting zone while the portion of the luminescent medium adjacent to the cathode forms an electron injecting and transporting zone. The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, a Frenkel exciton is formed. Recombination of this short-lived state may be visualized as an electron dropping from its conduction potential to a

valence band, with relaxation occurring, under certain conditions, preferentially via a photoemissive mechanism. Under this view of the mechanism of operation of typical thin-layer organic devices, the electroluminescent layer comprises a luminescence zone receiving mobile charge carriers (electrons and holes) from each electrode.

[0022] As noted above, light emission from OLEDs is typically via fluorescence or phosphorescence. There are issues with the use of phosphorescence. It has been noted that phosphorescent efficiency can decrease rapidly at high current densities. It may be that long phosphorescent lifetimes cause saturation of emissive sites, and triplet-triplet annihilation may also produce efficiency losses. Another difference between fluorescence and phosphorescence is that energy transfer of triplets from a conductive host to a luminescent guest molecule is typically slower than that of singlets; the long range dipole-dipole coupling (Förster transfer) which dominates energy transfer of singlets is (theoretically) forbidden for triplets by the principle of spin symmetry conservation. Thus, for triplets, energy transfer typically occurs by diffusion of excitons to neighboring molecules (Dexter transfer); significant overlap of donor and acceptor excitonic wavefunctions is critical to energy transfer. Another issue is that triplet diffusion lengths are typically long (e.g., >1400Å) compared with typical singlet diffusion lengths of about 200Å. Thus, if phosphorescent devices are to achieve their potential, device structures need to be optimized for triplet properties. In this invention, we exploit the property of long triplet diffusion lengths to improve external quantum efficiency.

[0023] Successful utilization of phosphorescence holds enormous promise for organic electroluminescent devices. For example, an advantage of phosphorescence is that all excitons (formed by the recombination of holes and electrons in an EL), which are (in part) triplet-based in phosphorescent devices, may participate in energy transfer and luminescence in certain electroluminescent materials. In contrast, only a small percentage of excitons in fluorescent devices, which are singlet-based, result in fluorescent luminescence.

[0024] An alternative is to use phosphorescence processes to improve the efficiency of fluorescence processes.. Fluorescence is in principle 75% less efficient due the three times higher number of symmetric excited states.

II.C. Background of materials

II.C.I. Basic heterostructures

[0025] Because one typically has at least one electron transporting layer and at least one hole transporting layer, one has layers of different materials, forming a heterostructure. The materials that produce the electroluminescent emission may be the same materials that function either as the electron transporting layer or as the hole transporting layer. Such devices in which the electron transporting layer or the hole transporting layer also functions as the emissive layer are referred to as having a single heterostructure. Alternatively, the electroluminescent material may be present in a separate emissive layer between the hole transporting layer and the electron transporting layer in what is referred to as a double heterostructure. The separate emissive layer may contain the emissive molecule doped into a host or the emissive layer may consist essentially of the emissive molecule.

[0026] That is, in addition to emissive materials that are present as the predominant component in the charge carrier layer, that is, either in the hole transporting layer or in the electron transporting layer, and that function both as the charge carrier material as well as the emissive material, the emissive material may be present in relatively low concentrations as a dopant in the charge carrier layer. Whenever a dopant is present, the predominant material in the charge carrier layer may be referred to as a host compound or as a receiving compound. Materials that are present as host and dopant are selected so as to have a high level of energy transfer from the host to the dopant material. In addition, these materials need to be capable of producing acceptable electrical properties for the OLED. Furthermore, such host and dopant materials are preferably capable of being incorporated into the OLED using materials that can be readily incorporated into the OLED by using convenient fabrication techniques, in particular, by using vacuum-deposition techniques.

II.C.2. Exciton blocking layer

[0027] One can have an exciton blocking layer in OLED devices to substantially block the diffusion of excitons, thus substantially keeping the excitons within the emission layer to enhance device efficiency. The material of blocking layer is characterized by an energy difference ("band gap") between its lowest unoccupied molecular orbital (LUMO) and its highest occupied molecular orbital (HOMO) This band gap substantially prevents the diffusion of excitons through the blocking layer, yet has only a minimal effect on the turn-on voltage of a completed electroluminescent device. The band gap is thus preferably greater than the energy level of excitons produced in an emission layer, such that such excitons are not able to exist in the blocking layer. Specifically, the band gap of the blocking layer is at least as great as the difference in energy between the triplet state and the ground state of the host.

[0028] For a situation with a blocking layer between a hole-conducting host and the electron transporting layer, one seeks the following characteristics, which are listed in order of relative importance.

EP 1 933 395 B1

1. The difference in energy between the LUMO and HOMO of the blocking layer is greater than the difference in energy between the triplet and ground state singlet of the host material.

2. Triplets in the host material are not quenched by the blocking layer.

3. The ionization potential (IP) of the blocking layer is greater than the ionization potential of the host. (Meaning that holes are held in the host.)

4. The energy level of the LUMO of the blocking layer and the energy level of the LUMO of the host are sufficiently close in energy such that there is less than 50% change in the overall conductivity of the device.

5. The blocking layer is as thin as possible subject to having a thickness of the layer that is sufficient to effectively block the transport of excitons from the emissive layer into the adjacent layer.

That is, to block excitons and holes, the ionization potential of the blocking layer should be greater than that of the HTL, while the electron affinity of the blocking layer should be approximately equal to that of the ETL to allow for facile transport of electrons.

[For a situation in which the emissive ("emitting") molecule is used without a hole transporting host, the above rules for selection of the blocking layer are modified by replacement of the word "host" by "emitting molecule."]

[0029] For the complementary situation with a blocking layer between a electron-conducting host and the hole-transporting layer one seeks characteristics (listed in order of importance):

1. The difference in energy between the LUMO and HOMO of the blocking layer is greater than the difference in energy between the triplet and ground state singlet of the host material.

2. Triplets in the host material are not quenched by the blocking layer.

3. The energy of the LUMO of the blocking layer is greater than the energy of the LUMO of the (electron-transporting) host. (Meaning that electrons are held in the host.)

4. The ionization potential of the blocking layer and the ionization potential of the host are such that holes are readily injected from the blocker into the host and there is less than a 50% change in the overall conductivity of the device.

5. The blocking layer is as thin as possible subject to having a thickness of the layer that is sufficient to effectively block the transport of excitons from the emissive layer into the adjacent layer.

[For a situation in which the emissive ("emitting") molecule is used without an electron transporting host, the above rules for selection of the blocking layer are modified by replacement of the word "host" by "emitting molecule."]

II.D. Color

[0030] As to colors, it is desirable for OLEDs to be fabricated using materials that provide electroluminescent emission in a relatively narrow band centered near selected spectral regions, which correspond to one of the three primary colors, red, green and blue so that they may be used as a colored layer in an OLED or SOLED. It is also desirable that such compounds be capable of being readily deposited as a thin layer using vacuum deposition techniques so that they may be readily incorporated into an OLED that is prepared entirely from vacuum-deposited organic materials.

[0031] U.S. 08/774,333, filed December 23, 1996 (allowed), is directed to OLEDs containing emitting compounds that produce a saturated red emission.

III. SUMMARY OF THE INVENTION

[0032] The present invention is directed to a phosphorescent organometallic compound of formula L_2IrX , wherein L and X are inequivalent bidentate ligands, X is a monoanionic bidentate ligand; and the L ligands are monoanionic bidentate ligands each coordinated to Ir (iridium) through an sp^2 hybridized carbon and a heteroatom.

[0033] According to an embodiment the heteroatom of the L ligands is nitrogen. According to a further embodiment the ring comprising the Ir, the sp^2 hybridized carbon, and the heteroatom of each of the L ligands consists of five atoms. According to a further embodiment the ring comprising the Ir, the Sp^2 hybridized carbon, and the heteroatom of each of the L ligands consists of six atoms. According to a further embodiment the X ligand is an O-O ligand. According to a

further embodiment the X ligand is an N-O ligand. According to a further embodiment L is selected from the group consisting of 2-(1-naphthyl)benzoxazole, 2-phenylbenzoxazole, 2-phenylbenzoxazole, 7,8-benzoquinoline, coumarin, thienylpyridine, phenylpyridines, benzothienylpyridine, 3-methoxy-2-phenylpyridine, tolylpyridine, phenylimines, vinylpyridines, pyridylpyrroles and pyridylimidazoles. According to a further embodiment the heteroatoms of the L ligands are in a trans configuration. According to a further embodiment X is selected from the group consisting of an acetylacetonate, a hexafluoroacetylacetonate, a salicylidene, a picolinate, a 8-hydroxyquinolate, amino acids, salicylaldehydes and iminoacetonates. According to a further embodiment the X ligand comprises an acetylacetonate.

[0034] According to a further embodiment a display device incorporates at least one of the previous compounds. According to a further embodiment the display device is incorporated into a system selected from the group of systems consisting of a vehicle, a computer, a television, a printer, a large area wall, a billboard, a stadium screen, a theatre screen and a sign.

[0035] According to a further embodiment previous compound is used in an organic light emitting device. According to a further embodiment previous compound is used in an emissive layer of an organic light emitting device.

IV. BRIEF DESCRIPTION OF THE DRAWINGS

[0036]

Figure 1. Expected structure of L_2IrX complexes along with the structure expected for **PPIr**. Four examples of X ligands used for these complexes are also shown. The structure shown is for an acac derivative. For the other X type ligands the O-O ligand would be replaced with an N-O ligand.

Ref. Figure 2. Comparison of facial and meridional isomers of L_3M .

Ref. Figure 3. Molecular formulae of mer isomers disclosed herewith: mer-Ir(ppy)₃ and mer-Ir(bq)₃. PPY (or ppy) denotes phenyl pyridyl and BQ (or bq) denotes 7,8-benzoquinoline.

Figure 4. Models of mer-Ir(ppy)₃ and (ppy)₂Ir(acac).

Figure 5. (a) Electroluminescent device data (quantum efficiency vs. current density) for 12% by mass "BTIr" in CBP. BTIr stands for bis (2-phenylbenzothiazole) iridium acetylacetonate. (b) emission spectrum from device

Figure 6. Representative molecule to trap holes.

Ref. Figure 7. Emission spectrum of Ir(3-MeOppy)₃

Figure 8. Emission spectrum of tpylrsd. Figure 9. Proton NMR spectrum of tpylrsd (=tpylrsd).

Figure 10. Emission spectrum of thpylrsd.

Figure 11. Proton NMR spectrum of thpylrsd.

Figure 12. Emission spectrum of btlrsd.

Figure 13. Proton NMR spectrum of btlrsd.

Figure 14. Emission spectrum of BQIr.

Figure 15. Proton NMR of BQIr.

Figure 16. Emission spectrum of BQIrFA. Figure 17. Emission spectrum of THIr (=thpy; THPIr).

Figure 18. Proton NMR spectrum of THPIr.

Figure 19. Emission spectra of PPIr.

Figure 20. Proton NMR spectrum of PPIr.

Figure 21. Emission spectrum of BTHPIr (=BTPIr)

Figure 22. Emission spectrum of tpyIr.

5 Figure 23. Crystal structure of tpyIr showing trans arrangement of nitrogen.

Figure 24. Emission spectrum of C6.

Figure 25. Emission spectrum of C6Ir.

10

Figure 26. Emission spectrum of PZIrP.

Figure 27. Emission spectrum of BONIr.

15

Figure 28. Proton NMR of BONIr.

Figure 29. Emission spectrum of BTIr.

Figure 30. Proton NMR of BTIr.

20

Figure 31. Emission spectrum of BOIr.

Figure 32. Proton NMR of BOIr.

25

Figure 33. Emission spectrum of BTIrQ.

Figure 34. Proton NMR spectrum of BTIrQ.

Figure 35. Emission spectrum of BTIRP.

30

Figure 36. Emission spectrum of BOIrP.

Figure 37. Emission of btlr type complexes with different ligands.

35

Figure 38. Proton NMR of mer-Irbq.

Figure 39. Other suitable L and X ligands for L₂MX compounds.

Figure 40. Examples of L L' L" M compounds.

40

V. DETAILED DESCRIPTION OF THE INVENTION

V.A. Chemistry

45 **[0037]** This invention is directed to the synthesis and use of certain organometallic molecules of formula L₂MX which may be doped into a host phase in an emitter layer of an organic light emitting diode. Optionally, the molecules of formula L₂MX may be used at elevated concentrations or neat in the emitter layer. This invention is further directed to an organic light emitting device comprising an emitter layer comprising a molecule of the formula L₂MX wherein L and X are inequivalent, bidentate ligands and M is a metal, preferably selected from the third row of the transition elements of the

50 periodic table, and most preferably Ir or Pt, which forms octahedral complexes and wherein the emitter layer produces an emission which has a maximum at a certain wavelength λ_{\max} .

V.A.1. Dopants

55 **[0038]** The general chemical formula for the molecules which are doped into the host phase is L₂MX, wherein M is a transition metal ion which forms octahedral complexes, L is a bidentate ligand, and X is a distinct bidentate ligand.

[0039] Examples of L are 2-(1-naphthyl)benzoxazole, (2-phenylbenzoxazole), (2-phenylbenzothiazole), (2-phenylbenzothiazole), (7,8-benzoquinoline), coumarin, (thienylpyridine), phenylpyridine, benzothienylpyridine, 3-methoxy-2-

phenylpyridine, thienylpyridine, and tolylpyridine.


[0040] Examples of X are acetylacetonate ("acac"), hexafluoroacetylacetonate, salicylidene, picolinate, and 8-hydroxyquinolate.

5 **[0041]** Further examples of L and X are given in Figure 39 and still further examples of L and X may be found in Comprehensive Coordination Chemistry, Volume 2, G. Wilkinson (editor-in-chief), Pergamon Press, especially in chapter 20.1 (beginning at page 715) by M. Calligaris and L. Randaccio and in chapter 20.4 (beginning at page 793) by R. S. Vagg.

V.A.2. Synthesis of molecules of formula L_2MX

10 V.A.2.a. Reaction scheme

[0042] The compounds of formula L_2MX can be made according to the reaction



15

wherein

$L_2M(\mu\text{-Cl})_2ML_2$ is a chloride bridged dimer with L a bidentate ligand, and M a metal such as Ir,

XH is a Bronsted acid which reacts with bridging chloride and serves to introduce a bidentate ligand X, where XH can be, for example, acetylacetone, hexafluoroacetylacetone, 2-picolinic acid, or N-methylsalicyclanilide.

20 L_2MX has approximate octahedral disposition of the bidentate ligands L, L, and X about M.

V.A.2.b. Examples

25 **[0043]** $L_2Ir(\mu\text{-Cl})_2IrL_2$ complexes were prepared from $IrCl_3 \cdot nH_2O$ and the appropriate ligand by literature procedures (S. Sprouse, K. A. King, P. J. Spellane, R. J. Watts, J. Am. Chem. Soc., 1984, 106, 6647-6653; for general reference: G. A. Carlson, et al., Inorg. Chem., 1993, 32, 4483; B. Schmid, et al., Inorg. Chem., 1993, 33, 9; F. Garces, et al.; Inorg. Chem., 1988, 27, 3464; M. G. Colombo, et al., Inorg. Chem., 1993, 32, 3088; A. Mamo, et al., Inorg. Chem., 1997, 36, 5947; S. Serroni, et al.; J. Am. Chem. Soc., 1994, 116, 9086; A. P. Wilde, et al., J. Phys. Chem., 1991, 95, 629; J. H. van Diemen, et al., Inorg. Chem., 1992, 31, 3518; M. G. Colombo, et al., Inorg. Chem., 1994, 33, 545)

30

Ref. example

35 **[0044]** **Ir(3-MeOppy)₃**. $Ir(acac)_3$ (0.57 g, 1.17 mmol) and 3-methoxy-2-phenylpyridine (1.3 g, 7.02 mmol) were mixed in 30 ml of glycerol and heated to 200°C for 24 hrs under N_2 . The resulting mixture was added to 100 ml of 1 M HCl. The precipitate was collected by filtration and purified by column chromatography using CH_2Cl_2 as the eluent to yield the product as bright yellow solids (0.35 g, 40%). MS (EI): m/z (relative intensity) 745 (M^+ , 100), 561 (30), 372 (35). Emission spectrum in Figure 7.

40 **[0045]** **tpylrds**. The chloride bridge dimer $(tpylrCl)_2$ (0.07 g, 0.06 mmol), salicylidene (0.022 g, 0.16 mmol) and Na_2CO_3 (0.02 g, 0.09 mmol) were mixed in 10 ml of 1,2-dichloroethane and 2 ml of ethanol. The mixture was refluxed under N_2 for 6 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the solvent evaporated. The excess salicylidene was removed by gentle heating under vacuum. The residual solid was redissolved in CH_2Cl_2 and the insoluble inorganic materials were removed by filtration. The filtrate was concentrated and column chromatographed using CH_2Cl_2 as the eluent to yield the product as bright yellow solids (0.07 g, 85%). MS (EI): m/z (relative intensity) 663 (M^+ , 75), 529 (100), 332 (35). The emission spectrum is in Figure 8 and the proton NMR spectrum is in Figure 9.

45 **[0046]** **thpylrds**. The chloride bridge dimer $(thpylrCl)_2$ (0.21 g, 0.19 mmol) was treated the same way as $(tpylrCl)_2$. Yield: 0.21 g, 84%. MS (EI): m/z (relative intensity) 647 (M^+ , 100), 513 (30), 486 (15), 434 (20), 324 (25). The emission spectrum is in Figure 10 and the proton NMR spectrum is in Figure 11.

50 **[0047]** **btlrds**. The chloride bridge dimer $(btlrCl)_2$ (0.05 g, 0.039 mmol) was treated the same way as $(tpylrCl)_2$. Yield: 0.05 g, 86%. MS (EI): m/z (relative intensity) 747 (M^+ , 100), 613 (100), 476 (30), 374 (25), 286 (32). The emission spectrum is in Figure 12 and the proton NMR spectrum is in Figure 13.

55 **[0048]** **Ir(bq)₂(acac), BQIr**. The chloride bridged dimer $(Ir(bq)_2Cl)_2$ (0.091 g, 0.078 mmol), acetylacetone (0.021 g) and sodium carbonate (0.083 g) were mixed in 10 ml of 2-ethoxyethanol. The mixture was refluxed under N_2 for 10 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the yellow precipitate filtered. The product was purified by flash chromatography using dichloromethane. Product: bright yellow solids (yield 91%). 1H NMR (360 MHz, acetone- d_6), ppm: 8.93 (d,2H), 8.47 (d,2H), 7.78 (m,4H), 7.25 (d,2H), 7.15 (d,2H), 6.87 (d,2H), 6.21 (d,2H), 5.70 (s,1H), 1.63 (s,6H). MS, e/z: 648 (M^+ , 80%), 549 (100%). The emission spectrum is in Figure 14 and the proton NMR spectrum is in Figure 15.

[0049] **Ir(bq)₂(Facac), BQIrFA**. The chloride bridged dimer $(Ir(bq)_2Cl)_2$ (0.091 g, 0.078 mmol), hexafluoroacetylacetone

EP 1 933 395 B1

(0.025 g) and sodium carbonate (0.083 g) were mixed in 10 ml of 2-ethoxyethanol. The mixture was refluxed under N₂ for 10 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the yellow precipitate filtered. The product was purified by flash chromatography using dichloromethane. Product: yellow solids (yield 69%). ¹H NMR (360 MHz, acetone-d₆), ppm: 8.99 (d,2H), 8.55 (d,2H), 7.86 (m,4H), 7.30 (d,2H), 7.14 (d,2H), 6.97 (d,2H), 6.13 (d,2H), 5.75 (s,1H). MS, e/z: 684 (M+,59%), 549 (100%). Emission spectrum in Figure 16.

[0050] Ir(thpy)₂(acac), THPIr. The chloride bridged dimer (Ir(thpy)₂Cl)₂ (0.082 g, 0.078 mmol), acetylacetonone (0.025 g) and sodium carbonate (0.083 g) were mixed in 10 ml of 2-ethoxyethanol. The mixture was refluxed under N₂ for 10 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the yellow precipitate filtered. The product was purified by flash chromatography using dichloromethane. Product: yellow-orange solid (yield 80%). ¹H NMR (360 MHz, acetone-d₆), ppm: 8.34 (d,2H), 7.79 (m,2H), 7.58 (d,2H), 7.21 (d,2H), 7.15 (d,2H), 6.07 (d,2H), 5.28 (s,1H), 1.70 (s,6H). MS, e/z: 612 (M+,89%), 513 (100%). The emission spectrum is in Figure 17 (noted "THIr") and the proton NMR spectrum is in Figure 18

[0051] Ir(ppy)₂(acac), PPIr. The chloride bridged dimer (Ir(ppy)₂Cl)₂ (0.080 g, 0.078 mmol), acetylacetonone (0.025 g) and sodium carbonate (0.083 g) were mixed in 10 ml of 2-ethoxyethanol. The mixture was refluxed under N₂ for 10 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the yellow precipitate filtered. The product was purified by flash chromatography using dichloromethane. Product: yellow solid (yield 87%). ¹H NMR (360 MHz, acetone-d₆), ppm: 8.54 (d,2H), 8.06 (d,2H), 7.92 (m,2H), 7.81 (d,2H), 7.35 (d,2H), 6.78 (m,2H), 6.69 (m,2H), 6.20 (d,2H), 5.12 (s,1H), 1.62 (s,6H). MS, e/z: 600 (M+,75%), 501 (100%). The emission spectrum is in Figure 19 and the proton NMR spectrum is in Figure 20.

[0052] Ir(bthpy)₂(acac), BTPIr. The chloride bridged dimer (Ir(bthpy)₂Cl)₂ (0.103 g, 0.078 mmol), acetylacetonone (0.025 g) and sodium carbonate (0.083 g) were mixed in 10 ml of 2-ethoxyethanol. The mixture was refluxed under N₂ for 10 hrs or until no dimer was revealed by TLC. The reaction was then cooled and the yellow precipitate filtered. The product was purified by flash chromatography using dichloromethane. Product: yellow solid (yield 49%). MS, e/z: 712 (M+,66%), 613 (100%). Emission spectrum is in Figure 21.

[0053] [Ir(ptpy)₂Cl]₂. A solution of IrCl₃·xH₂O (1.506g, 5.030 mmol) and 2-(p-tolyl)pyridine (3.509 g, 20.74 mmol) in 2-ethoxyethanol (30 mL) was refluxed for 25 hours. The yellow-green mixture was cooled to room temperature and 20 mL of 1.0 M HCl was added to precipitate the product. The mixture was filtered and washed with 100 mL of 1.0 M HCl followed by 50 mL of methanol then dried. The product was obtained as a yellow powder (1.850 g, 65%).

[0054] [Ir(ppz)₂Cl]₂. A solution of IrCl₃·xH₂O (0.904 g, 3.027 mmol) and 1-phenylpyrazole (1.725 g, 11.96 mmol) in 2-ethoxyethanol (30 mL) was refluxed for 21 hours. The gray-green mixture was cooled to room temperature and 20 mL of 1.0 M HCl was added to precipitate the product. The mixture was filtered and washed with 100 mL of 1.0 M HCl followed by 50 mL of methanol then dried. The product was obtained as a light gray powder (1.133 g, 73%).

[0055] [Ir(C6)₂Cl]₂. A solution of IrCl₃·xH₂O (0.075 g, 0.251 mmol) and coumarin C6 [3-(2-benzothiazolyl)-7-(diethyl) coumarin] (Aldrich) (0.350 g, 1.00 mmol) in 2-ethoxyethanol (15 mL) was refluxed for 22 hours. The dark red mixture was cooled to room temperature and 20 mL of 1.0 M HCl was added to precipitate the product. The mixture was filtered and washed with 100 mL of 1.0 M HCl followed by 50 mL of methanol. The product was dissolved in and precipitated with methanol. The solid was filtered and washed with methanol until no green emission was observed in the filtrate. The product was obtained as an orange powder (0.0657 g, 28%).

[0056] Ir(ptpy)₂acac (tpyIr). A solution of [Ir(ptpy)₂Cl]₂ (1.705 g, 1.511 mmol), 2,4-pentanedione (3.013g, 30.08 mmol) and (1.802 g, 17.04 mmol) in 1,2-dichloroethane (60 mL) was refluxed for 40 hours. The yellow-green mixture was cooled to room temperature and the solvent was removed under reduced pressure. The product was taken up in 50 mL of CH₂Cl₂ and filtered through Celite. The solvent was removed under reduced pressure to yield orange crystals of the product (1.696 g, 89%). The emission spectrum is given in Figure 22. The results of an x-ray diffraction study of the structure are given in Figure 23. One sees that the nitrogen atoms of the tpy ("tolyl pyridyl") groups are in a trans configuration. For the x-ray study, the number of reflections was 4663 and the R factor was 5.4%.

[0057] Ir(C6)₂acac (C6Ir). Two drops of 2,4-pentanedione and an excess of Na₂CO₃ was added to solution of [Ir(C6)₂Cl]₂ in CDCl₃. The tube was heated for 48 hours at 50 °C and then filtered through a short plug of Celite in a Pasteur pipet. The solvent and excess 2,4-pentanedione were removed under reduced pressure to yield the product as an orange solid. Emission of C6 in Figure 24 and of C6Ir in Figure 25.

[0058] Ir(ppz)₂picolinate (PZIr). A solution of [Ir(ppz)₂Cl]₂ (0.0545 g, 0.0530 mmol) and picolinic acid (0.0525 g, 0.426 mmol) in CH₂Cl₂ (15 mL) was refluxed for 16 hours. The light green mixture was cooled to room temperature and the solvent was removed under reduced pressure. The resultant solid was taken up in 10 mL of methanol and a light green solid precipitated from the solution. The supernatant liquid was decanted off and the solid was dissolved in CH₂Cl₂ and filtered through a short plug of silica. The solvent was removed under reduced pressure to yield light green crystals of the product (0.0075 g, 12%). Emission in Figure 26.

[0059] 2-(1-naphthyl)benzoxazote, (BZO-Naph). (11.06g, 101 mmol) of 2-aminophenol was mixed with (15.867g, 92.2mmol) of 1-naphthoic acid in the presence of polyphosphoric acid. The mixture was heated and stirred at 240°C under N₂ for 8 hrs. The mixture was allowed to cool to 100°C, this was followed by addition of water. The insoluble

EP 1 933 395 B1

residue was collected by filtration, washed with water then reslurried in an excess of 10 % Na₂CO₃. The alkaline slurry was filtered and the product washed thoroughly with water and dried under vacuum. The product was purified by vacuum distillation. BP 140°C /0.3 mmHg. Yield 4.8 g (21%).

[0060] Tetrakis(2-(1-napbtbyl)benzoxazole C², M)(μ-dichloro)diiridium. ((Ir₂(BZO-Naph)₄Cl)₂). Iridium trichloride hydrate (0.388 g) was combined with 2-(1-naphthyl)benzoxazole (1.2 g, 4.88 mmol), The mixture was dissolved in 2-ethoxyethanol (30 mL) then refluxed for 24 hrs. The solution was cooled to room temperature, the resulting orange solid product was collected in a centrifuge tube. The dimer was washed with methanol followed by chloroform through four cycles of centrifuge/redispersion cycles. Yield 0.66g

[0061] Bis(2-(1-napbtbyl)benzoxazole) acetylacetonate, Ir(BZO-Naph)₂(acac), (BONIr). The chloride bridged dimer (Ir₂(BZO-Naph)₄Cl)₂ (0.66 g, 0.46 mmol), acetylacetonate (0.185 g) and sodium carbonate (0.2 g) were mixed in 20 ml of dichloroethane. The mixture was refluxed under N₂ for 60 hrs. The reaction was then cooled and the orange/red precipitate was collected in centrifuge tube. The product was washed with water/methanol (1:1) mixture followed by methanol wash through four cycles of centrifuge/redispersioncycles. The orange/red solid product was purified by sublimation. SP 250°C/2x10⁻⁵ torr.yield 0.57g (80%). The emission spectrum is in Figure 27 and the proton NMR spectrum is in Figure 28.

[0062] Bis(2-phenylbenzothiazole) Iridium acetylacetonate (BTIr): 9.8 mmol (0.98g, 1.0mL) of 2,4-pentanedione was added to a room-temperature solution of 2.1 mmol 2-phenylbenzothiazole Iridium chloride dimer (2.7g) in 120mL of 2-ethoxyethanol. Approximately 1g of sodium carbonate was added, and the mixture was heated to reflux under nitrogen in an oil bath for several hours. Reaction mixture was cooled to room temperature, and the orange precipitate was filtered off via vacuum. The filtrate was concentrated and methanol was added to precipitate more product. Successive filtrations and precipitations afforded a 75%yield. The emission spectrum is in Figure 29 and the proton NMR spectrum is in Figure 30 .

[0063] Bis(2-phenylbenzoxazole) Iridium acac (BOIr): 9.8 mmol (0.98g, 1.0mL) of 2,4-pentanedione was added to a room-temperature solution of 2.4 mmol 2-phenylbenzoxazole Iridium chloride dimer (3.0g) in 120mL of 2-ethoxyethanol. Approximately 1g of sodium carbonate was added, and the mixture was heated to reflux under nitrogen in an oil bath overnight (~16hrs.). Reaction mixture was cooled to room temperature, and the yellow precipitate was filtered off via vacuum. The filtrate was concentrated and methanol was added to precipitate more product. Successive filtrations and precipitations afforded a 60%yield. The emission spectrum is in Figure 31 and the proton NMR spectrum is in Figure 32.

[0064] Bis(2-phenylbenzothiazole) Iridium (8-hydroxyquinolate) (BTIrQ): 4.7 mmol (0.68g) of 8-hydroxyquinoline was added to a room-temperature solution of 0.14 mmol 2-phenylbenzothiazole Iridium chloride dimer (0.19g) in 20mL of 2-ethoxyethanol. Approximately 700mg of sodium carbonate was added, and the mixture was heated to reflux under nitrogen in an oil bath overnight (23hrs.). Reaction mixture was cooled to room temperature, and the red precipitate was filtered off via vacuum. The filtrate was concentrated and methanol was added to precipitate more product. Successive filtrations and precipitations afforded a 57%yield. The emission spectrum is in Figure 33 and the proton NMR spectrum is in Figure 34.


[0065] Bis(2-phenylbenzothiazole) Iridium picolinate (BTIrP): 2.14 mmol (0.26g) of picolinic acid was added to a room-temperature solution of 0.80 mmol 2-phenylbenzothiazole Iridium chloride dimer (1.0g) in 60mL of dichloromethane. The mixture was heated to reflux under nitrogen in an oil bath for 8.5 hours. The reaction mixture was cooled to room temperature, and the yellow precipitate was filtered off via vacuum. The filtrate was concentrated and methanol was added to precipitate more product. Successive filtrations and precipitations yielded about 900mg of impure product. Emission spectrum is in Figure 35.

[0066] Bis(2-phenylbenzoxazole) Iridium picolinate (BOIrP): 0.52 mmol (0.064g) of picolinic acid was added to a room-temperature solution of 0.14 mmol 2-phenylbenzoxazole Iridium chloride dimer (0.18g) in 20mL of dichloromethane. The mixture was heated to reflux under nitrogen in an oil bath overnight (17.5hrs.). Reaction mixture was cooled to room temperature, and the yellow precipitate was filtered off via vacuum. The precipitate was dissolved in dichloromethane and transferred to a vial, and the solvent was removed. Emission spectrum is in Figure 36.


[0067] Comparative emission spectra for different L' in btlr complexes are in Figure 37.

V.A.2.c. Advantages over the prior art


[0068] This synthesis has certain advantages over the prior art. Compounds of formula PtL₃ cannot be sublimed without decomposition. Obtaining compounds of formula IrL₃ can be problematic. Some ligands react cleanly with Ir(acac)₃ to give the tris complex, but more than half of the ligands we have studied do not react cleanly in the reaction:




typically 30% yield, L=2-phenylpyridine, benzoquinoline, 2-thienylpyridine A preferred route to Ir complexes can be through the chloride-bridged dimer L₂M(μ-Cl)₂ML₂ via



Although fewer than 10% of the ligands we have studied failed to give the Ir dimer cleanly and in high yield, the conversion of the dimer into the tris complex IrL_3 is problematic working for only a few ligands.



[0069] We have discovered that a far more fruitful approach to preparing phosphorescent complexes is to use chloride bridged dimers to create emitters. The dimer itself does not emit strongly, presumably because of strong self quenching by the adjacent metal (e.g., iridium) atoms. We have found that the chloride ligands can be replaced by a chelating ligand to give a stable, octahedral metal complex through the chemistry:



[0070] We have extensively studied the system wherein M = iridium. The resultant iridium complexes emit strongly, in most cases with lifetimes of 1-3 microseconds (" μsec "). Such a lifetime is indicative of phosphorescence (see Charles Kittel, Introduction to Solid State Physics). The transition in these materials is a metal ligand charge transfer ("MLCT").




[0071] In the Detailed Discussion below, we analyze data of emission spectra and lifetimes of a number of different complexes, all of which can be characterized as L_2MX (M=Ir), where L is a cyclometallated (bidentate) ligand and X is a bidentate ligand. In nearly every case, the emission in these complexes is based on an MLCT transition between Ir and the L ligand or a mixture of that transition and an intraligand transition. Specific examples are described below. Based on theoretical and spectroscopic studies, the complexes have an octahedral coordination about the metal (for example, for the nitrogen heterocycles of the L ligand, there is a trans disposition in the Ir octahedron).

[0072] Specifically, in Figure 1, we give the structure for L_2IrX , wherein L = 2-phenyl pyridine and X = acac, picolinate (from picolinic acid), salicylanilide, or 8-hydroxyquinolate.

V.A.2.d. Facial vs. meridional isomers

[0073] A slight variation of the synthetic route to make L_2IrX allows formation of meridional isomers of formula L_3Ir . The L_3Ir complexes that have been disclosed previously all have a facial disposition of the chelating ligands. Herewith, we disclose the formation and use of meridional L_3Ir complexes as phosphors in OLEDs. The two structures are shown in the Figure 2.

[0074] The facial L_3Ir isomers have been prepared by the reaction of L with $\text{Ir}(\text{acac})_3$ in refluxing glycerol as described in equation 1 (below). A preferred route into L_3Ir complexes is through the chloride bridged dimer ($\text{L}_2\text{Ir}(\mu\text{-Cl})_2\text{IrL}_2$), equation 2+3 (below). The product of equation 3 is a facial isomer, identical to the one formed from $\text{Ir}(\text{acac})_3$. The benefit of the latter prep is a better yield of facial- L_3Ir . If the third ligand is added to the dimer in the presence of base and acetylacetone (no Ag^+) a good yield of the meridional isomer is obtained. The meridional isomer does not convert to the facial one on recrystallization, refluxing in coordinating solvents or on sublimation. Two examples of these meridional complexes have been formed, mer-Irppy and mer-Irbq (Figure 3), however, we believe that any ligand that gives a stable facial- L_3Ir can be made into a meridional form as well.



[0075] Surprisingly, the photophysics of the meridional isomers is different from that of the facial forms. This can be seen in the details of the spectra discussed below, which show a marked red shift and broadening in the meridional isomer relative to its facial counterpart. The emission lines appear as if a red band has been added to the and characteristic of the facial- L_3Ir . The structure of the meridional isomer is similar to those of L_2IrX complexes, with respect, for example,

to the arrangement of the N atoms of the ligands about Ir. Specifically, for L=ppy ligands, the nitrogen of the L ligand is trans in both mer-Ir(ppy)₃ and in (ppy)₂Ir(acac). Further, one of the L ligands for the mer-L₃Ir complexes has the same coordination as the X ligand of L₂IrX complexes. In order to illustrate this point a model of mer-Ir(ppy)₃ is shown next to (ppy)₂Ir(acac) in Figure 4. One of the ppy ligands of mer-Ir(ppy)₃ is coordinated to the Ir center in the same geometry as the acac ligand of (ppy)₂Ir(acac).

[0076] The HOMO and LUMO energies of these L₃Ir molecules are clearly affected by the choice of isomer. These energies are very important in controlling the current-voltage characteristics and lifetimes of OLEDs prepared with these phosphors.

[0077] The syntheses for the two isomers depicted in Figure 3 are as follows.


Syntheses of meridional isomers:

[0078] **mer-Ir(bq)**: 91 mg (0.078 mmol) of [Ir(bq)2Cl]2 dimer, 35.8 mg (0.2 mmol) of 7,8-benzoquinoline, 0.02 ml of acetylacetone (ca. 0.2 mmol) and 83 mg (0.78 mmol) of sodium carbonate were boiled in 12 ml of 2-ethoxyethanol (used as received) for 14 hours in inert atmosphere. Upon cooling yellow-orange precipitate forms and is isolated by filtration and flash chromatography (silica gel, CH₂Cl₂) (yield 72%). ¹H NMR (360 MHz, dichloromethane-d₂), ppm: 8.31 (q, 1H), 8.18 (q, 1H), 8.12 (q, 1H), 8.03 (m, 2H), 7.82 (m, 3H), 7.59 (m, 2H), 7.47 (m, 2H), 7.40 (d, 1H), 7.17 (m, 9H), 6.81 (d, 1H), 6.57 (d, 1H). MS, m/z: 727 (100%, M+). NMR spectrum in Figure 38.

[0079] **mer-Ir(tpy)₃**: A solution of IrCl₃·xH₂O (0.301 g, 1.01 mmol), 2-(p-tolyl)pyridine (1.027 g, 6.069 mmol), 2,4-pentanedione (0.208 g, 2.08 mmol) and Na₂CO₃ (0.350 g, 3.30 mmol) in 2-ethoxyethanol (30 mL) was refluxed for 65 hours. The yellow-green mixture was cooled to room temperature and 20 mL of 1.0 M HCl was added to precipitate the product. The mixture was filtered and washed with 100 mL of 1.0 M HCl followed by 50 mL of methanol then dried and the solid was dissolved in CH₂Cl₂ and filtered through a short plug of silica. The solvent was removed under reduced pressure to yield the product as a yellow-orange powder (0.265 g, 38%).


V.A.3. Potential host molecules

[0080] This invention is directed toward the use of the above-noted dopants in a host phase. This host phase may be comprised of molecules comprising a carbazole moiety. Molecules which fall within the scope of the invention are included in the following.



[A line segment denotes possible substitution at any available carbon atom or atoms of the indicated by ring by alkyl or aryl groups.]

[0081] An additional preferred molecule with a carbazole functionality is 4,4'-N,N'-dicarbazole-biphenyl (CBP), which has the formula



V.B.1. Utilization in devices

[0082] The device structure that we chose to use is very similar to the standard vacuum deposited one. As an overview, a hole transporting layer ("HTL") is first deposited onto the ITO (indium tin oxide) coated glass substrate. For the device yielding 12% quantum efficiency, the HTL consisted of 30 nm (300 Å) of NPD. Onto the NPD a thin film of the organometallic doped into a host matrix is deposited to form an emitter layer. In the example, the emitter layer was CBP with 12% by weight bis(2-phenylbenzothiazole) iridium acetylacetonate (termed "BTIr"); the layer thickness was 30 nm (300 Å). A blocking layer is deposited onto the emitter layer. The blocking layer consisted of bathocuproine ("BCP"), and the thickness was 20 nm (200 Å). An electron transport layer is deposited onto the blocking layer. The electron transport layer consisted of Alq3 of thickness 20nm. The device is finished by depositing a Mg-Ag electrode onto the electron transporting layer. This was of thickness 100nm. All of the depositions were carried out at a vacuum less than 5×10^{-5} Torr. The devices were tested in air, without packaging.

[0083] When we apply a voltage between the cathode and the anode, holes are injected from ITO to NPD and transported by the NPD layer, while electrons are injected from MgAg to Alq and transported through Alq and BCP. Then holes and electrons are injected into EML and carrier recombination occurs in CBP, the excited states were formed, energy transfer to BTIr occurs and finally BTIr molecules are excited and decay radiatively.

[0084] As illustrated in Figure 5, the quantum efficiency of this device is 12% at a current density of about 0.01 mA/cm².

[0085] Pertinent terms are as follows:

ITO is a transparent conducting phase of indium tin oxide which functions as an anode.


ITO is a degenerate semiconductor formed by doping a wide band semiconductor. The carrier concentration of the ITO is in excess of $10^{19}/\text{cm}^3$.

BCP is an exciton blocking and electron transport layer.


Alq3: electron injection layer.

Other hole transport layer materials could be used. For example, TPD, a hole transport layer, can be used.

[0086] BCP functions as an electron transport layer and as an exciton blocking layer, which layer has a thickness of about 10 nm (100 Å). BCP is 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (also called bathocuproine) which has the formula



[0087] The Alq3, which functions as an electron injection/electron transport layer has the following formula.



Alq₃

In general, the doping level is varied to establish the optimum doping level.

V. B. 2. Incorporation of a fluorescent ligand into a phosphorescent complex

[0088] As noted above, fluorescent materials have certain advantages as emitters in devices. If the L ligand that is used in making the L₂MX (for example, M=Ir) complex has a high fluorescent quantum efficiency, it is possible to use the strong spin orbit coupling of the Ir metal to efficiently intersystem cross in and out of the triplet states of the ligands. The concept is that the Ir makes the L ligand an efficient phosphorescent center. Using this approach, it is possible to take any fluorescent dye and make an efficient phosphorescent molecule from it (that is, L fluorescent but L₂MX (M=Ir) phosphorescent).

[0089] As an example, we prepared a L₂IrX wherein L=coumarin and X=acac. We refer to this as coumarin-6 ["C6Ir"]. The complex gives intense orange emission, whereas coumarin by itself emits green. Both coumarin and C6Ir spectra are given in the figures.

[0090] Other fluorescent dyes would be expected to show similar spectral shifts. Since the number of fluorescent dyes that have been developed for dye lasers and other applications is quite large, we expect that this approach would lead to a wide range of phosphorescent materials.

[0091] One needs a fluorescent dye with suitable functionality such that it can be metallated by the metal (for example, iridium) to make a 5 or 6 membered metallocycle. All of the L ligands we have studied to date have sp² hybridized carbons and heterocyclic N atoms in the ligands, such that one can form a five membered ring on reacting with Ir.

V.B.3. Carrier trapping at X or L ligands

[0092] Potential degradation reactions, involving holes or electrons, can occur in the emitter layer. The resultant oxidation or reduction can alter the emitter, and degrade performance.

[0093] In order to get the maximum efficiency for phosphor doped OLEDs, it is important to control the holes or electrons which lead to undesirable oxidation or reduction reactions. One way to do this is to trap carriers (holes or electrons) at the phosphorescent dopant. It may be beneficial to trap the carrier at a position remote from the atoms or ligands responsible for the phosphorescence. The carrier that is thus remotely trapped could readily recombine with the opposite carrier either intramolecularly or with the carrier from an adjacent molecule.

[0094] An example of a phosphor designed to trap holes is shown in Figure 6. The diarylamine group on the salicylanilide group is expected to have a HOMO level 200-300 mV above that of the Ir complex (based on electrochemical measurements), leading to the holes being trapped exclusively at the amine groups. Holes will be readily trapped at the amine, but the emission from this molecule will come from MLCT and intraligand transitions from the Ir(phenylpyridine) system. An electron trapped on this molecule will most likely be in one of the pyridyl ligands. Intramolecular recombination will lead to the formation of an exciton, largely in the Ir(phenylpyridine) system. Since the trapping site is on the X ligand, which is typically not involved extensively in the luminescent process, the presence of the trapping site will not greatly affect the emission energy for the complex. Related molecules can be designed in which electron carriers are trapped

remoted to the L_2Ir system.

V.B.4. Color Tuning

- 5 **[0095]** As found in the IrL_3 system, the emission color is strongly affected by the L ligand. This is consistent with the emission involving either MLCT or intraligand transitions. In all of the cases that we have been able to make both the tris complex (i.e., IrL_3) and the L_2IrX complex, the emission spectra are very similar. For example $Ir(ppy)_3$ and $(ppy)_2Ir(acac)$ (acronym = **PPIr**) give strong green emission with a λ_{max} of 510 nm. A similar trend is seen in comparing $Ir(BQ)_3$ and $Ir(thpy)_3$ to their $L_2Ir(acac)$ derivatives, i.e. , in some cases, no significant shift in emission between the two complexes.
- 10 **[0096]** However, in other cases, the choice of X ligand affects both the energy of emission and efficiency. Acac and salicylanilide L_2IrX complexes give very similar spectra. The picolinic acid derivatives that we have prepared thus far show a small blue shift (15 nm) in their emission spectra relative to the acac and salicylanilide complexes of the same ligands. This can be seen in the spectra for **BTIr**, **BTIrsd** and **BTIrpc**. In all three of these complexes we expect that the emission becomes principally form MLCT and Intra-L transitions and the picolinic acid ligands are changing the energies of the metal orbitals and thus affecting the MLCT bands.
- 15 **[0097]** If an X ligand is used whose triplet levels fall lower in energy than the " L_2Ir " framework, emission from the X ligand can be observed. This is the case for the BTIRQ complex. In this complex the emission intensity is very weak and centered at 650 nm. This was surprising since the emission for the BT ligand based systems are all near 550 nm. The emission in this case is almost completely form Q based transitions. The phosphorescence spectra for heavy metal quinolates (e.g. IrQ_3 or PtQ_2) are centered at 650 nm. The complexes themselves emit with very low efficiency, < 0.01 . Both the energy and efficiency of the L_2IrQ material is consistent "X" based emission. If the emission form the X ligand or the "IrX" system were efficient this could have been a good red emitter. It is important to note that while all of the examples list here are strong "L" emitters, this does not preclude a good phosphor from being formed from "X" based emission.
- 20 **[0098]** The wrong choice of X ligand can also severally quench the emission from L_2IrX complexes. Both hexafluoroacac and diphenyl-acac complexes give either very weak emission or no emission at all when used as the X ligand in L_2IrX complexes. The reasons why these ligands quench emission so strong are not at all clear, one of these ligands is more electron withdrawing than acac and the other more electron donating. We give the spectrum for **BQIrFA** in the figures . The emission spectrum for this complex is slightly shifted from **BQIr**, as expected for the much stronger electron withdrawing nature of the hexafluoroacac ligand. The emission intensity from **BQIrFA** is at least 2 orders of magnitude weaker than **BQIr**. We have not explored the complexes of these ligands due this severe quenching problem.
- 25 **[0099]** The wrong choice of X ligand can also severally quench the emission from L_2IrX complexes. Both hexafluoroacac and diphenyl-acac complexes give either very weak emission or no emission at all when used as the X ligand in L_2IrX complexes. The reasons why these ligands quench emission so strong are not at all clear, one of these ligands is more electron withdrawing than acac and the other more electron donating. We give the spectrum for **BQIrFA** in the figures . The emission spectrum for this complex is slightly shifted from **BQIr**, as expected for the much stronger electron withdrawing nature of the hexafluoroacac ligand. The emission intensity from **BQIrFA** is at least 2 orders of magnitude weaker than **BQIr**. We have not explored the complexes of these ligands due this severe quenching problem.
- 30 **[0099]** The wrong choice of X ligand can also severally quench the emission from L_2IrX complexes. Both hexafluoroacac and diphenyl-acac complexes give either very weak emission or no emission at all when used as the X ligand in L_2IrX complexes. The reasons why these ligands quench emission so strong are not at all clear, one of these ligands is more electron withdrawing than acac and the other more electron donating. We give the spectrum for **BQIrFA** in the figures . The emission spectrum for this complex is slightly shifted from **BQIr**, as expected for the much stronger electron withdrawing nature of the hexafluoroacac ligand. The emission intensity from **BQIrFA** is at least 2 orders of magnitude weaker than **BQIr**. We have not explored the complexes of these ligands due this severe quenching problem.

V. C. Other molecular depictions

- 35 **[0099]** CBP was used in the device described herein. The invention will work with other hole-transporting molecules known by one of ordinary skill to work in hole transporting layers of OLEDs.
- [0100]** Specifically, the invention will work with other molecules comprising a carbazole functionality, or an analogous aryl amine functionality.

40 V.D. Uses of device

- [0101]** The OLED of the present invention may be used in substantially any type of device which is comprised of an OLED, for example, in OLEDs that are incorporated into a larger display, a vehicle, a computer, a television, a printer, a large area wall, theater or stadium screen, a billboard or a sign.
- 45 **[0102]** The present invention as disclosed herein may be used in conjunction with copending applications: "High Reliability, High Efficiency, Integratable Organic Light Emitting Devices and Methods of Producing Same", Serial No. 08/774,119 (filed December 23, 1996); "Novel Materials for Multicolor Light Emitting Diodes", Serial No. 08/850,264 (filed May 2, 1997); "Electron Transporting and Light Emitting Layers Based on Organic Free Radicals", Serial No. 08/774,120 (filed December 23, 1996)(issued as US 5,811,833 on Sept. 22, 1998); "Multicolor Display Devices", Serial No. 08/772,333 (filed December 23, 1996); "Red-Emitting Organic Light Emitting Devices (OLED's)", Serial No. 08/774,087 (filed December 23, 1996)(allowed); "Driving Circuit For Stacked Organic Light Emitting Devices", Serial No. 08/792,050 (filed February 3, 1997)(issued as US 5,757,139 on May 26, 1998); "High Efficiency Organic Light Emitting Device Structures", Serial No. 08/772,332 (filed December 23, 1996)(issued as US 5,834,893 on Nov. 10, 1998); "Vacuum Deposited, Non-Polymeric Flexible Organic Light Emitting Devices", Serial No. 08/789,319 (filed January 23, 1997) (issued as US 5,844,363 on Dec. 1, 1998); "Displays Having Mesa Pixel Configuration", Serial No. 08/794,595 (filed February 3, 1997); "Stacked Organic Light Emitting Devices", Serial No. 08/792,046 (filed February 3, 1997)(issued as US 5,917,280 on June 29, 1999); "High Contrast Transparent Organic Light Emitting Devices", Serial No. 08/792,046 (filed February 3, 1997); "High Contrast Transparent Organic Light Emitting Device Display", Serial No. 08/821,380 (filed
- 55

March 20, 1997); "Organic Light Emitting Devices Containing A Metal Complex of 5-Hydroxy-Quinoxaline as A Host Material", Serial No. 08/838,099 (filed April 15, 1997)(issued as US 5,861,219 on Jan. 19, 1999); "Light Emitting Devices Having High Brightness", Serial No. 08/844,353 (filed April 18, 1997); "Organic Semiconductor Laser", Serial No. 08/859,468 (filed May 19, 1997); "Saturated Full Color Stacked Organic Light Emitting Devices", Serial No. 08/858,994 (filed on May 20, 1997)(issued as US 5,932,895 on Aug. 3, 1999); "Plasma Treatment of Conductive Layers", PCT/US97/10252, (filed June 12, 1997); "Novel Materials for Multicolor Light Emitting Diodes", Serial No. 08/814,976, (filed Mar. 11, 1997); "Novel Materials for Multicolor Light Emitting Diodes", Serial No. 08/771,815, (filed Dec. 23, 1996); "Patterning of Thin Films for the Fabrication of Organic Multi-color Displays", PCT/US97/10289, (filed June 12, 1997), and "Double Heterostructure Infrared and Vertical Cavity Surface Emitting Organic Lasers", PCT/US98/09480 filed May 8, 1998; US 5,874,803 issued Feb. 23, 1999; US 5,707,745 issued Jan. 13, 1998; US 5,703,436 issued Dec. 30, 1997; and US 5,757,026 issued May 26, 1998.

Claims

1. Phosphorescent organometallic compound of formula L_2IrX , wherein L and X are inequivalent bidentate ligands, X is a monoanionic bidentate ligand; and the L ligands are monoanionic bidentate ligands each coordinated to Ir (iridium) through an sp^2 hybridized carbon and a heteroatom.
2. The compound according to claim 1, wherein the heteroatom of the L ligands is nitrogen.
3. The compound according to claim 1 or 2, wherein the ring comprising the Ir, the sp^2 hybridized carbon, and the heteroatom of each of the L ligands consists of five atoms.
4. The compound according to claim 1, 2 or 3, wherein the ring comprising the Ir, the sp^2 hybridized carbon, and the heteroatom of each of the L ligands consists of six atoms.
5. The compound according to claim 2, wherein the X ligand is an O-O ligand.
6. The compound according to claim 2, wherein the X ligand is an N-O ligand.
7. The compound according to any one of the previous claims, wherein L is selected from the group consisting of 2-(1-naphthyl)benzoxazole, 2-phenylbenzoxazole, 2-phenylbenzoxazole, 7,8-benzoquinoline, coumarin, thienylpyridine, phenylpyridines, benzothienylpyridine, 3-methoxy-2-phenylpyridine, tolylpyridine, phenylimines, vinylpyridines, pyridylpyrroles; and pyridylimidazoles.
8. The compound according to any one of the previous claims, wherein the heteroatoms of the L ligands are in a trans configuration.
9. The compound according to any one of the previous claims, wherein X is selected from the group consisting of an acetylacetonate, a hexafluoroacetylacetonate, a salicylidene, a picolinate, a 8-hydroxyquinolate, amino acids, salicylaldehydes and iminoacetonates.
10. The compound according to any one of claims 1 to 5 and 7 to 9, wherein the X ligand comprises an acetylacetonate.
11. A display device incorporating at least one of the compounds according to any one of the previous claims.
12. The display device according to claim 11, wherein the display device is incorporated into a system selected from the group of systems consisting of a vehicle, a computer, a television, a printer, a large area wall, a billboard, a stadium screen, a theatre screen and a sign.
13. Use of a compound according to any one of the claims 1 through 10 in an organic light emitting device.
14. Use of a compound according to any one of the claims 1 through 10 in an emissive layer of an organic light emitting device.

Patentansprüche

1. Phosphoreszierende organometallische Verbindung der Formel L_2IrX ,
 worin
 5 L und X nicht äquivalente zweizählige Liganden sind,
 X ein monoanionischer zweizähliger Ligand ist;
 und
 die L Liganden monoanionische zweizählige Liganden sind, die jeweils durch ein sp^2 -hybridisiertes Kohlenstoffatom
 und ein Heteroatom mit Ir (Iridium) koordiniert sind.
 10
2. Die Verbindung nach Anspruch 1, worin das Heteroatom der L-Liganden Stickstoff ist.
3. Die Verbindung nach Anspruch 1 oder 2, worin der Ring umfassend das Ir, das sp^2 -hybridisierte Kohlenstoffatom
 und das Heteroatom jedes der L-Liganden aus fünf Atomen besteht.
 15
4. Die Verbindung nach Anspruch 1, 2 or 3, worin der Ring umfassend das Ir, das sp^2 -hybridisierte Kohlenstoffatom
 und das Heteroatom jedes der L-Liganden aus sechs Atomen besteht.
5. Die Verbindung nach Anspruch 2, worin der X-Ligand ein O-O-Ligand ist.
 20
6. Die Verbindung nach Anspruch 2, worin der X-Ligand ein N-O-Ligand ist.
7. Die Verbindung nach einem der vorhergehenden Ansprüche, worin L aus der Gruppe ausgewählt ist, die aus 2-(1-
 Naphthyl)benzoxazol, 2-Phenylbenzoxazol, 2-Phenylbenzoxazol, 7,8-Benzochinolin, Cumarin, Thienylpyridin, Phe-
 25 nylpyridinen, Benzothienylpyridin, 3-Methoxy-2-phenylpyridin, Tolylypyridin, Phenyliminen, Vinylpyridinen, Pyridyl-
 pyrrolen und Pyridylimidazolen besteht.
8. Die Verbindung nach einem der vorhergehenden Ansprüche, worin sich die Heteroatome der L-Liganden in einer
 trans-Konfiguration befinden.
 30
9. Die Verbindung nach einem der vorhergehenden Ansprüche, worin X aus der Gruppe ausgewählt ist, die aus einem
 Acetylacetonat, einem Hexafluoroacetylacetonat, einem Salicyliden, einem Pikolinat, einem 8-Hydroxychinolinat,
 Aminosäuren, Salicylaldehyden und Iminoacetonaten besteht.
- 35 10. Die Verbindung nach einem der Ansprüche 1 bis 5 und 7 bis 9, worin der X-Ligand ein Acetylacetonat umfasst.
11. Eine Anzeige- oder Displayeinrichtung, die wenigstens eine der Verbindungen nach einem der vorhergehenden
 Ansprüche verkörpert.
- 40 12. Die Anzeige- oder Displayeinrichtung nach Anspruch 11, worin diese Einrichtung in einem System verkörpert ist,
 das aus der Gruppe von Systemen ausgewählt ist, die aus einem Fahrzeug, einem Computer, einem Fernseher,
 einem Drucker, einer großflächige Wand, einer Reklamefläche, einem Stadion-Bildschirm, einem Theater-Bildschirm
 und einer Hinweistafel oder einem Schild besteht.
- 45 13. Verwendung einer Verbindung nach einem der Ansprüche 1 bis 10 in einer organischen lichtemittierenden Einrich-
 tung.
14. Verwendung einer Verbindung nach einem der Ansprüche 1 bis 10 in einer emittierenden Schicht einer organischen
 lichtemittierenden Einrichtung.
 50

Revendications

1. composé organométallique phosphorescent de formule L_2IrX , où L et X sont des ligands bidentés non équivalents,
 55 X est un ligand bidenté mono-anionique ; et
 les ligands L sont des ligands bidentés mono-anioniques coordonnés chacun à Ir (iridium) par l'intermédiaire d'un
 carbone hybridé sp^2 et d'un hétéroatome.

EP 1 933 395 B1

2. Composé selon la revendication 1, dans lequel l'hétéroatome des ligands L est l'azote.
3. Composé selon la revendication 1 ou 2, dans lequel l'anneau comprenant le Ir, le carbone hybridé sp^2 et l'hétéroatome de chacun des ligands L est composé de cinq atomes.
- 5 4. Composé selon la revendication 1, 2 ou 3, dans lequel l'anneau comprenant le Ir, le carbone hybridé sp^2 et l'hétéroatome de chacun des ligands L est composé de six atomes.
- 10 5. Composé selon la revendication 2, dans lequel le ligand X est un ligand o-o.
6. Composé selon la revendication 2, dans lequel le ligand X est un ligand N-O.
- 15 7. Composé selon l'une quelconque des revendications précédentes, dans lequel L est choisi parmi le groupe composé de 2-(1-naphthyle)benzoxazole, 2-phénylbenzoxazole, 2-phénylbenzoxazole, 7,8-benzoquinoline, coumarine, thiénylpyridine, phénylpyridines, benzothiénylpyridine, 3-méthoxy-2-phénylpyridine, tolylpyridine, phénylimines, vinylpyridines, pyridylpyrroles et pyridylimidazoles.
- 20 8. Composé selon l'une quelconque des revendications précédentes, dans lequel les hétéroatomes des ligands L sont en configuration trans.
9. Composé selon l'une quelconque des revendications précédentes, dans lequel X est choisi parmi le groupe composé d'un acétylacétionate, d'un hexafluoroacétylacétionate, d'un salicylidène, d'un picolinate, d'un 8-hydroxyquinolinate, d'acides aminés, de salicylaldéhydes et d'iminoacétonates.
- 25 10. Composé selon l'une quelconque des revendications 1 à 5 et 7 à 9, dans lequel le ligand X comprend un acétylacétionate.
- 30 11. Dispositif d'affichage incorporant au moins l'un des composés selon l'une quelconque des revendications précédentes.
- 35 12. Dispositif d'affichage selon la revendication 11, dans lequel le dispositif d'affichage est incorporé dans un système choisi parmi le groupe de systèmes constitués d'un véhicule, d'un ordinateur, d'un téléviseur, d'une imprimante, d'un grand panneau mural, d'un panneau d'affichage, d'un écran de stade, d'un écran de cinéma et d'un panneau de signalisation.
- 40 13. Utilisation d'un composé selon l'une quelconque des revendications 1 à 10 dans un dispositif organique luminescent.
- 45 14. Utilisation d'un composé selon l'une quelconque des revendications 1 à 10 dans une couche émissive d'un dispositif organique luminescent.
- 50
- 55




Fig. 1




Fig. 2





Fig. 3






Fig. 5A




Fig. 5B




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20




Fig. 21




Fig. 22

Crystal structure of tpylr




Fig. 23




Fig. 24




Fig. 25




Fig. 26




Fig. 27




Fig. 28




Fig. 29




Fig. 30




Fig. 31




Fig. 32




Fig. 33




Fig. 34




Fig. 35




Fig. 36




Fig. 37






Fig. 38


other L ligands




phenylimines




vinylpyridines




arylquinolines




pyridynaphthalenes



pyridylpyroles




pyridylimidazoles




phenylindoles


other X ligands



aminoacids



salicylaldehydes



iminoacetates





Fig. 39


Fig. 40

LL'L''M




M(ppy)(bq)(thpy)

LL'MX




M(ppy)(bq)(acac)



M(ppy)(thpy)(acac)

LMXX'



M(ppy)(sd)(acac)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 9515790 W [0002] [0004]
- US 9702681 W [0003]
- US 08774333 B [0031]
- WO 08774119 A [0102]
- WO 08850264 A [0102]
- WO 08774120 A [0102]
- US 5811833 A [0102]
- WO 08772333 A [0102]
- WO 08774087 A [0102]
- WO 08792050 A [0102]
- US 5757139 A [0102]
- WO 08772332 A [0102]
- US 5834893 A [0102]
- WO 08789319 A [0102]
- US 5844363 A [0102]
- WO 08794595 A [0102]
- WO 08792046 A [0102]
- US 5917280 A [0102]
- WO 08821380 A [0102]
- WO 08838099 A [0102]
- US 5861219 A [0102]
- WO 08844353 A [0102]
- WO 08859468 A [0102]
- WO 08858994 A [0102]
- US 5932895 A [0102]
- US 9710252 W [0102]
- WO 08814976 A [0102]
- WO 08771815 A [0102]
- US 9710289 W [0102]
- US 9809480 W [0102]
- US 5874803 A [0102]
- US 5707745 A [0102]
- US 5703436 A [0102]
- US 5757026 A [0102]

Non-patent literature cited in the description

- **C.W. TANG et al.** *Appl. Phys. Lett.*, 1987, vol. 51, 913 [0002]
- **S.R. FORREST ; P.E. BURROWS ; M.E. THOMPSON.** *Laser Focus World*, February 1995 [0002]
- **M.A. BALDO ; D. F. O'BRIEN ; M.E. THOMPSON ; S. R. FORREST.** Very high-efficiency green organic light-emitting devices based on electrophosphorescence. *Applied Physics Letters*, 1999, vol. 75, 4-6 [0005]
- **C.H. CHEN ; J. SHI ; C.W. TANG.** Recent developments in molecular organic electroluminescent materials. *Macromolecular Symposia*, 1997, vol. 125, 1-48 [0007]
- **U. BRACKMANN.** *Lambdachrome Laser Dyes*, 1997 [0007]
- **M. A. BALDO et al.** High efficiency phosphorescent emission from organic electroluminescent devices. *Nature*, 1998, vol. 395, 151-154 [0007]
- **M. A. BALDO ; M. E. THOMPSON ; S.R. FORREST.** An analytic model of triplet-triplet annihilation in electrophosphorescent devices. *Nature*, 1999 [0007]
- **D.L. DEXTER.** A theory of sensitized luminescence in solids. *J. Chem. Phys.*, 1953, vol. 21, 836-850 [0016]
- **E. WIGNER ; E.W. WITTMER.** Über die Struktur der zweiatomigen Molekelspektren nach der Quantenmechanik. *Zeitschrift für Physik*, 1928, vol. 51, 859-886 [0016]
- **M. KLESSINGER ; J. MICHL.** Excited states and photochemistry of organic molecules. VCH Publishers, 1995 [0016]
- **T. FÖRSTER.** *Zwischenmolekulare Energiewanderung und Fluoreszenz*, *Annalen der Physik*, 1948, vol. 2, 55-75 [0016]
- **T. FÖRSTER.** Fluoreszenz organischer Verbindungen. Vandenhoeck and Ruprecht, 1951 [0016]
- **F WILKINSON.** *Advances in Photochemistry*. John Wiley & Sons, 1964, 241-268 [0017]
- **T. FÖRSTER.** Transfer mechanisms of electronic excitation. *Discussions of the Faraday Society*, 1959, vol. 27, 7-17 [0017]
- **V.L. ERMOLAEV ; E. B. SVESHNIKOVA.** Inductive-resonance transfer of energy from aromatic molecules in the triplet state. *Doklady Akademii Nauk SSSR*, 1963, vol. 149, 1295-1298 [0017]
- **M. A. BALDO et al.** *Appl. Phys. Lett.*, 1999, vol. 75, 4-6 [0018]
- **C. W. TANG ; S. A. VANSLYKE ; C. H. CHEN.** Electroluminescence of doped organic films. *J. Appl. Phys.*, 1989, vol. 65, 3610-3616 [0018]
- **V. BULOVIĆ et al.** Bright, saturated, red-to-yellow organic light-emitting devices based on polarization-induced spectral shifts. *Chem. Phys. Lett.*, 1998, vol. 287, 455-460 [0018]

EP 1 933 395 B1

- **M. CALLIGARIS ; L. RANDACCIO.** Comprehensive Coordination Chemistry. Pergamon Press, vol. 2, 715 [0041]
- **R. S. VAGG.** Comprehensive Coordination Chemistry. Pergamon Press, 793 [0041]
- **S. SPROUSE ; K. A. KING ; P. J. SPELLANE ; R. J. WATTS.** *J. Am. Chem. Soc.*, 1984, vol. 106, 6647-6653 [0043]
- **G. A. CARLSON et al.** *Inorg. Chem.*, 1993, vol. 32, 4483 [0043]
- **B. SCHMID et al.** *Inorg. Chem.*, 1993, vol. 33, 9 [0043]
- **F. GARCES et al.** *Inorg. Chem.*, 1988, vol. 27, 3464 [0043]
- **M. G. COLOMBO et al.** *Inorg. Chem.*, 1993, vol. 32, 3088 [0043]
- **A. MAMO et al.** *Inorg. Chem.*, 1997, vol. 36, 5947 [0043]
- **S. SERRONI et al.** *J. Am. Chem. Soc.*, 1994, vol. 116, 9086 [0043]
- **A. P. WILDE et al.** *J. Phys. Chem.*, 1991, vol. 95, 629 [0043]
- **J. H. VAN DIEMEN et al.** *Inorg. Chem.*, 1992, vol. 31, 3518 [0043]
- **M. G. COLOMBO et al.** *Inorg. Chem.*, 1994, vol. 33, 545 [0043]